

Qualifications:

Spring-Fast Specifications	BAP Series Flexi-Grommet™
Axis Conformity	Multi
Vicat Softening Point per ASTM D01525 Rate B	TPE Cushion: ISO306 Color: Gray 230°F (110°C)
Operating Temperature Range	-40°F to 185°F (-40°C to 85°C)
Dielectric Strength per NASM22529, Section 3.2.1	1500 Volts at 60Hz
Substrate	Stainless Steel
Taber Abrasion Resistance	TPE Cushion: per D1044 1Kg load, C17 Wheel 25mg loss 1000 cycles
Finish	TPE Cushion
Salt Spray Hours per ASTM B117 MIL-STD-202, Method 301	2000 hours
Immersion	Per NASM22529 and Skydrol Compatible
Random Shock & Vibration	MIL-STD-1344, Method 2005.1 Test Condition VI, Letter J Duration 8 hours longitudinal and 8 hours perpendicular. rms G 41.7
Flammability	FAR 25.601, FAR 25.853 MIL-STD-202F, Method 111A UL94 V-0 File No. E113553 NZMT2
Fabrication Options	Factory pre-cut lengths or private branded kits Roll-Fast™ application tool Full Bypass Shears Spring-Fast Cutter Cart